



35W

FIBERGLASS
FABRIC SPECIFICATIONS

Weldfire Protective Welding Products

Physical Characteristics

Fiber Content	Fiberglass
Coating/Finish	n.a.
Color	White
Weight	35 oz/yd ²
Thickness	0.065"
Weave	Plain
Flexibility	Excellent
Electrical	Non-conductive
Chemical	Non-reactive
Widths	40" & 60"

Performance Characteristics

Break Strength [warp]	300 lbs.
Break Strength [fill]	250 lbs.
Tear Strength [warp]	n.a.
Tear Strength [fill]	n.a.
Flame Resistance	Non-flammable
Afterglow	5 seconds max
Char Length	n.a.

Temperature Parameters

Service	1000°F
Maximum	1200°F
Melt	>1200°F

- Provides excellent protection from welding sparks and spatter

Thermostatic Industries, Inc. (800) 345-4217

Fax: (213) 749-2646 E-mail: thermo@thermostatic.com

Website: <http://www.thermostatic.com>